

LUCALOR RY123G343

CPVC Compound for Injection Molding of Fittings

Technical Data Sheet

	Values	Units	Standards
SPECIFIC GRAVITY	1.51	g/cm ³	ISO 1183
VICAT SOFTENING TEMPERATURE (under 5 daN)	104	°C	ISO 306
TENSILE STRESS AT YIELD	50	MPa	ISO 527-2
TENSILE STRESS AT BREAK	50	MPa	ISO 527-2
TENSILE MODULUS OF ELASTICITY	2 710	MPa	ISO 527-2
CHARPY IMPACT STRENGTH	11	kJ/m ²	ISO 179
OXYGEN INDEX	65	%	ISO 4589-2
FLAMMABILITY UL 94	V-0	-	ISO 1210
WATER ABSORPTION (24h at 23°C)	0.030	mg/cm ²	ISO 62

Comments

- CPVC Compound for Injection Molding of Fittings & Accessories (Grey)
- Developed to manufacture fittings meeting all the requirements of ISO 15877-3
- Cell Class **23447-B** (according to ASTM D 1784)

The information contained in this document is based on trials carried out by our Research Centres and data selected from the literature, but shall in no event be held to constitute or imply any warranty, undertaking, express or implied commitment on our part. Our formal specifications define the limit of our commitment. No liability whatsoever can be accepted by Arkema with regard to the handling, processing or use of the product or products concerned which must in all cases be employed in accordance with all relevant laws and/or regulations in force in the country or countries concerned.

PVC Business Unit
 Quai Louis Aulagne, BP 35
 69191 St Fons Cedex
www.arkema.com

Réf.	Édition n°	Date
BU PVC	3.0	06/2008

info.lacovyl@arkema.com
www.lacovyl.com